



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 0 472 089 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**06.05.1999 Bulletin 1999/18**

(51) Int Cl.<sup>6</sup>: **C09B 67/40**

(21) Application number: **91113546.5**

(22) Date of filing: **13.08.1991**

(54) **Dye suspensions**

Farbstoff Suspensionen

Suspensions de colorants

(84) Designated Contracting States:  
**AT BE CH DE DK ES FR GB GR IT LI LU NL SE**

(30) Priority: **15.08.1990 GB 9017924**  
**22.02.1991 GB 9103772**

(43) Date of publication of application:  
**26.02.1992 Bulletin 1992/09**

(73) Proprietor: **ALBRIGHT & WILSON UK LIMITED**  
**Oldbury, Warley, West Midlands B68 0NN (GB)**

(72) Inventors:  
• **Haslop, William Paul**  
**Hensingham, Cumbria CA28 8XZ (GB)**  
• **Newton, Jill Elizabeth**  
**Nr. Stourbridge, West Midlands DY8 5NU (GB)**  
• **Clapperton, Richard Malcolm**  
**Belbroughton, Stourbridge, West Midlands (GB)**

(74) Representative:  
**Savidge, Roger Gordon Madgwick et al**  
**ALBRIGHT & WILSON UK LIMITED**  
**Patents Department**  
**P O Box 3**  
**210-222 Hagley Road**  
**Oldbury, Warley, West Midlands B68 0NN (GB)**

(56) References cited:  
**EP-A- 0 225 287 US-A- 4 110 073**  
**US-A- 4 218 218**

- **PATENT ABSTRACTS OF JAPAN, unexamined applications, C field, vol. 12, no. 496, December 23, 1988 THE PATENT OFFICE JAPANESE GOVERNMENT page 104 C 555**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 472 089 B1**

**Description**

[0001] The present invention provides a novel means of suspending relatively water-soluble dyestuffs such as disperse dyes and optical bleaches in aqueous media without the need to employ environmentally harmful solvents, and without the need for spray drying or handling dust producing powders.

[0002] Dyestuffs, and in particular disperse dyes, are often required as concentrated aqueous suspensions of solid for use either as printing pastes or for dilution to form dyebaths. A problem with the suspensions available hitherto for the latter purpose has been poor storage stability, leading to sedimentation on standing. The properties required for effective printing pastes have also proved difficult to obtain by conventional means. The past must be capable of easy extrusion, but must not run after application to the fabric. This requires a strongly thixotropic medium. Finally, the excess paste must be readily removed by rinsing. Pastes which are currently available present problems on rinsing.

[0003] Optical bleaches are sparingly soluble fluorescent dyes used in detergents to make laundered fabrics look brighter. They are conveniently supplied to the detergent formulator as spray dried powders which are expensive to dry and cause potential hazards in handling due to dust formation. They are added typically to detergent slurries for spray drying or to liquid laundry detergents. Accurate addition of the powder to the slurry or liquid and even dispersion may present problems.

[0004] We have discovered that substantially water-insoluble or sparingly soluble disperse dyes may be suspended in concentrations of 2 to 50% by weight in aqueous structured surfactant systems. The expression "structured surfactant system" refers to aqueous systems comprising surfactant structures larger than conventional spherical micelles, which interact to confer thixotropic properties on the aqueous medium. The structures may be solid, mesophase or liquid and may be in the form of multi-layered spherulites, rods or discs or lamellae discontinuously dispersed or emulsified in the system or forming weak reticular structures

[0005] The size of the structures may typically lie within the range 0.01 to 200 microns, preferably 0.5 to 20 microns. Structured surfactant systems are usually formed by the interaction of surfactants with dissolved electrolyte salts or bases. Such systems are present in some liquid detergents and cleaning compositions and have been described, for instance, in GB-2,123,846 and GB-A-2,153,380.

[0006] Use of structured surfactants to suspend dyestuffs offers a number of potential advantages. The structured surfactants are capable of suspending a wide range of particle sizes and may be adapted to a wide range of pH e.g. by appropriate choice of surfactant. The systems are generally obtainable in a shear stable form which facilitates wet milling, are physically storage stable over a wide range of temperatures and disperse readily to form stable dye baths. They can readily be incorporated in detergents e.g. by addition to slurries for spray drying or by mixing into liquid detergent formulations. Also very high payloads can be achieved in formulations which are easy and safe to handle.

[0007] Our invention provides a dye suspension comprising 2% to 50% by weight of particles or droplets of a sparingly water soluble or substantially water-insoluble dye stably dispersed in a pourable medium; characterised in that: said medium comprises water, at least 2% by weight based on the total weight of the composition of surfactant and, if required, sufficient of a surfactant desolubilising electrolyte, to form with said surfactant a structured surfactant system comprising a G-phase or a dispersion of surfactant mesophase, lamellar solid, or multi-layered spherulites so as to confer thixotropic and solid-suspending properties. Preferably said dyes are disperse dyes or optical bleaches.

[0008] Preferably the product may be a dispersed or reticular lamellar structure such as those described in GB-2 123 846 or most preferably a spherulitic structure such as those described in GB-A-2 153 380. Other structures which may be present include G-phase, viscous isotropic phase, M-phase, and a mixture of phases.

**Surfactants**

[0009] The compositions of our invention preferably contain at least 2%, more usually at least 4%, e.g. at least 5% by weight of surfactants. The surfactants may constitute up to about 65% by weight of the composition, although we prefer on economic grounds to use lower concentrations e.g. less than 50%, preferably less than 45%, e.g. 8 to 30% by weight especially 10 to 20.

[0010] The surfactant may for example consist substantially of an at least sparingly water-soluble salt of sulphonic or mono esterified sulphuric acids e.g. an alkylbenzene sulphonate, alkyl sulphate, alkyl ether sulphate, olefin sulphonate, alkane sulphonate, alkylphenol sulphate, alkylphenol ether sulphate, alkylethanolamide sulphate, alkylethanolamide ether sulphate, or alpha sulphonyl fatty acid or its esters each having at least one alkyl or alkenyl group with from 8 to 22, more usually 10 to 20, aliphatic carbon atoms. Said alkyl or alkenyl groups are preferably straight chain primary groups but may optionally be secondary, or branched chain groups. The expression "ether" hereinbefore refers to oxyalkylene and homo- and mixed polyoxyalkylene groups such as polyoxyethylene, polyoxypropylene, glyceryl and mixed polyoxyethylene-oxypropylene or mixed glyceryl-oxyethylene, glyceryl-oxypropylene groups, or glyceryl-oxyethylene-oxypropylene groups, typically containing from 1 to 20 oxyalkylene groups. For example, the sulphonated or sulphated surfactant may be sodium or isopropylammonium dodecyl benzene sulphonate, potassium hexadecyl ben-

zene sulphonate, sodium dodecyl dimethyl benzene sulphonate, sodium lauryl sulphate, sodium tallow sulphate, potassium oleyl sulphate, ammonium lauryl monoethoxy sulphate, sodium lauryl triethoxy sulphate, or monethanolamine cetyl 10 mole ethoxylate sulphate.

[0011] Other anionic surfactants useful according to the present invention include fatty alkyl sulposuccinates, fatty alkyl ether sulposuccinates, fatty alkyl sulposuccinamates, fatty alkyl ether sulposuccinamates, acyl sarcosinates, acyl taurides, isethionates, soaps such as stearates, palmitates, resinates, oleates, linoleates, rosins soaps and alkyl ether carboxylates and saponins.

[0012] Anionic phosphate esters including naturally occurring surfactants such as lecithin may also be used.

[0013] In each case the anionic surfactant typically contains at least one aliphatic hydrocarbon chain having from 8 to 22 preferably 10 to 20 usually an average of 12 to 18 carbon atoms, an ionisable acidic group such as a sulphonyl, acid sulphate, carboxy, phosphono- or acid phosphate group, and, in the case of ethers, one or more glyceryl and/or from 1 to 20 ethyleneoxy and/or propyleneoxy groups.

[0014] Preferred anionic surfactants are amine salts, e.g. salts of monoethanolamine, diethanolamine, triethanolamine and alkyl amines containing up to seven aliphatic carbon atoms, such as isopropylamine. Other salts of commercial interest include those of sodium potassium, lithium, calcium, magnesium and ammonium.

[0015] The surfactant may optionally contain or consist of nonionic surfactants. The nonionic surfactant may be e.g. a C<sub>10-22</sub> alkanolamide of a mono or di- lower alkanolamine, such as coconut or tallow monoethanolamide or diethanolamide. Other nonionic surfactants which may optionally be present, include ethoxylated alcohols, ethoxylated carboxylic acids, ethoxylated amines, ethoxylated amides, ethoxylated alkylolamides, ethoxylated alkylphenols, ethoxylated glyceryl esters, ethoxylated sorbitan esters, ethoxylated phosphate esters, and the propoxylated, butoxylated and mixed ethoxy/propoxy and/or butoxy analogues of all the aforesaid ethoxylated nonionics, all having a C<sub>8-22</sub> alkyl or alkenyl group and up to 20 ethyleneoxy and/or propyleneoxy and/or butyleneoxy groups, or any other nonionic surfactant which has hitherto been incorporated in powder or liquid detergent compositions e.g. amine oxides. The latter typically have at least one C<sub>8-22</sub>, preferably C<sub>10-20</sub> alkyl or alkenyl group and up to two lower (e.g. C<sub>1-4</sub>, preferably C<sub>1-2</sub>) alkyl groups. Other non-ionic surfactants include alkyl polyglucosides.

[0016] The preferred nonionics for our invention are for example those having an HLB range of 6-18 e.g. 8-12.

[0017] Our compositions may contain cationic surfactants, which include quaternary amines having at least one long chain (e.g. C<sub>12-22</sub> typically C<sub>16-20</sub>) alkyl or alkenyl group optionally one benzyl group and the remainder of the four substituents short chain (e.g. C<sub>1-4</sub>) alkyl groups. They also include imidazolines and quaternised imidazolines having at least one long chain alkyl or alkenyl group, and amido amines and quaternised amido amines having at least one long chain alkyl or alkenyl group. The quaternised surfactants are all usually salts of anions which impart a measure of water solubility such as formate, acetate, lactate, tartrate, chloride, methosulphate, ethosulphate, sulphate or nitrate.

[0018] Compositions of our invention may also contain one or more amphoteric surfactant, which include betaines, sulphobetaines and phosphobetaines formed by reacting a suitable tertiary nitrogen compound having a long chain alkyl or alkenyl group with the appropriate reagent, such as chloroacetic acid or propane sultone. Examples of suitable tertiary nitrogen containing compounds include: tertiary amines having one or two long chain alkyl or alkenyl groups and optionally a benzyl group, any other substituent being a short chain alkyl group; imidazolines having one or two long chain alkyl or alkenyl groups and amidoamines having one or two long chain alkyl or alkenyl groups.

[0019] The specific surfactant types described above are only exemplary of the commoner surfactants suitable for use according to the invention. Any surfactant capable of forming a structured system may be included. A fuller description of the principal types of surfactant which are commercially available is given in "Surface Active Agents and Detergents" by Schwartz Perry and Berch.

### Electrolyte

[0020] Dissolved electrolyte compounds are optional constituents of our compositions. For the purposes of this specification "electrolyte" means any water soluble, ionisable, non-surface-active compound which tends to desolubilise or "salt out" surfactants from solution or micellar solution.

[0021] Although it is preferred to prepare structured systems in the absence of electrolyte, if the surfactant concentration is sufficiently high, the mobility of such systems is sometimes insufficient unless the surfactant has been selected with great care. Addition of electrolyte permits the preparation of mobile structured systems containing relatively low concentrations of surfactant.

[0022] The electrolyte may be present in concentrations up to saturation. Typically the less the amount of surfactant present, the more electrolyte may be required to form a structure capable of supporting solid materials. We generally prefer to select the cheapest electrolytes on economic grounds. Thus electrolyte could typically be present in a concentration of at least 1% by weight based on the total weight of the composition, e.g. at least 2%, especially at least 3%. Usually the concentration is less than 30% more usually less than 15% e.g. less than 10% by weight. Typically where electrolytes are required, the concentration is from 3% to 4%.

[0023] The maximum electrolyte concentration depends, among other things, on the type of structure, and the viscosity required as well as considerations of cost. We prefer to form spherulitic systems as described in our application GB-A-2,153,380 in order to obtain a satisfactory balance between mobility and high payload of suspended dyestuff. The optimum concentration of electrolyte for any particular type and amount of surfactant may be ascertained as described in our aforesaid application by observing the variation of electrical conductivity with increasing electrolyte concentration until the first conductivity minimum is observed.

[0024] Preferably the concentration of surfactant and/or electrolyte is adjusted to provide a composition which is non-sedimenting on standing for three months at ambient temperature, or at 0°C or 50°C. Preferably also said content is adjusted to provide a shear stable composition and, desirably, one which does not increase viscosity substantially after exposure to normal shearing.

[0025] Alternatively sufficient surfactant/electrolyte may be added to form a lamellar system as described in GB-2,123,846, e.g. by adding enough electrolyte to ensure that the liquid suspending medium separates on centrifuging at 800G for seventeen hours to form a lye phase containing little or no surfactant. The amount of water in the formulation may then be adjusted to obtain an optimum balance of mobility and stability. Lamellar systems are preferred for suspending certain optical bleaches which tend to destabilise spherulitic systems.

[0026] In addition to cost, choice of electrolyte may depend on the intended use of the suspension. Dye suspensions preferably contain non-toxic electrolytes, or concentrations insufficiently high to give rise to ill effects. Compositions may contain auxiliary or synergistic materials as the electrolyte or part thereof. The selected electrolyte should also be chemically compatible with the substance to be suspended. Typical electrolytes for use in the present invention include alkali metal, alkaline earth metal, ammonium or amine salts including chlorides, bromides, iodides, fluorides, orthophosphates, condensed phosphates, phosphonates, sulphates, bicarbonate, carbonates, borates, nitrates, chlorates, chromates, formates, acetates, oxalates, citrates, lactates, tartrates, silicates, hypochlorites and, if required to adjust the pH, e.g. to improve the stability of the suspended solid or dispersed liquid or lower the toxicity, acids or bases such as hydrochloric, sulphuric, phosphoric or acetic acids, or sodium, potassium, ammonium or calcium hydroxides, or alkaline silicates.

[0027] Electrolytes which form insoluble precipitates with the surfactants or which give rise to the formation of large crystals e.g. more than 1mm on standing are preferably avoided. Thus, for example, concentrations of sodium sulphate close to its saturation concentration in the composition at room temperature are undesirable.

### Suspended Dyestuff

[0028] The particle or droplet size of the suspended material may vary widely. The maximum size that can be stably suspended depends upon the density of the suspended phase and the Yield Point of the suspending medium. However, for practical purposes we prefer that the maximum particle size is less than 1mm, preferably less than 500 microns. Most preferably the mean particle size and majority of the particles are in the range 0.005 to 2.5 microns e.g. 0.01 to 2, especially 0.01 to 1 microns.

[0029] Where the dyestuff is a low melting solid, it is sometimes desirable to incorporate a small amount of a melting point depressant to inhibit phase changes during manufacture or storage of the composition. Such changes may give rise to instability.

[0030] The proportion of the suspended phase can vary between 2 and 50%. The proportion depends on the intended use of the concentrate, higher proportions (e.g. 15 to 40%) being preferred where the concentrate is to be dispersed in water to form a dyebath or added to a detergent formulation and lower concentrations (e.g. 2 to 15%) when the concentrate is to be used directly as a printing paste.

[0031] The viscosity of the suspensions at 21sec<sup>-1</sup> shear is typically from 0.001 to 50 Pascal seconds e.g. 0.1 Pascal seconds, preferably 0.2 to 0.5 Pascal seconds.

[0032] The dyestuff is typically a disperse dye or an optical bleach (optical brightening agent or OBA) for use in laundry detergents.

[0033] Typical examples of OBA's which may be used in the present invention include: ethoxylated 1, 2-(benzimidazole) ethylene; 2-styrylnaphth[1,2d]oxazole; 1,2-bis(5' methyl-2-benzoxazole) ethylene; disodium-4,4' -bis (6-methylethanolamine-3 -aniline-1,3, 5-triazin-2'-yl)-2,2'-stilbene sulphonate; N-(2-hydroxyethyl-4, 4'-bis(benzimidazole)stilbene; tetrasodium -hydroxyethyl)-amino-6\*(3"-sulphophenyl) amino-1", 3", 5"-triazin-2"-yl amino]-2,2'-stilbenedisulphonate; disodium-4-(6"-sulphonaphtho [1',2'-d]triazol-2-yl)-2-stilbene sulphonate; disodium-4,4'-bis [4"-(2"-hydroxy ethoxy)-6"-amino-1",3",5"-triazin-2"-yl amino]-2, 2'- stilbenedisulphonate; 4-methyl-7dimethyl aminocoumarin; and alkoxyated 4,4'-bis(benzimidazole) stilbene.

### Crystal Growth and Stability

[0034] One problem which arises with many suspensions of dyestuffs in water is lack of stability due to crystal growth

or chemical interaction between the suspended dyestuff and the aqueous medium and/or other components of the formulation. For instance pairs of dyestuffs which act complementarily may be chemically incompatible when stored together in aqueous concentrates.

[0035] The present invention provides according to a preferred embodiment a method of protecting dyestuffs suspended in an aqueous based formulation against interaction with the aqueous suspending medium or with other components of the formulation. We have discovered that dyestuffs encapsulated in water soluble encapsulants such as water soluble film-forming polymers, may be stably suspended in aqueous structured liquids and, surprisingly, retain their activity to a substantial degree on storage.

[0036] Encapsulation in water soluble film forming polymers and gums is a well known technique for binding a wide variety of sensitive ingredients, including pharmaceuticals and enzymes, and protecting them from deterioration during storage in air. Such capsules are conventionally used in an aqueous medium, which dissolves the capsule and releases the active ingredient immediately prior to use. It is not, therefore, on the face of it, possible to use such capsules to afford protection on storage in aqueous media.

[0037] We believe that water soluble capsules in structured liquids are surprisingly stable in the presence of relatively high electrolyte contents. Electrolyte is sometimes required to interact with surfactants, which usually form a spherulitic or lamellar structure capable of suspending insoluble particles.

[0038] The suspending properties of a structured liquid detergent assist in preventing the protected dyestuff from undergoing agglomeration and sedimentation. We believe the electrolyte also prevents the dissolution of the water soluble capsules.

[0039] The latter protect the dyestuffs until the formulation is diluted for use, when the electrolyte is diluted sufficiently for the capsule to dissolve and release the dye.

[0040] According to one embodiment our invention provides an aqueous based dyestuff formulation comprising an aqueous suspending medium having suspended therein particles or droplets of a disperse dye encapsulated in or coacervated with a water soluble encapsulant which is insoluble in said aqueous suspending medium. Preferably the aqueous suspending medium comprises a surfactant and sufficient electrolyte to form the surfactant into a structure capable of supporting suspended solid particles and preventing dissolution of the encapsulant.

[0041] According to a preferred embodiment our invention provides a method of encapsulating or coacervating disperse dyes suspended in an aqueous structured surfactant, containing dissolved electrolyte, which comprises adding an aqueous solution of encapsulant thereto. The dye and the encapsulant may be added together to the aqueous surfactant either before, after or simultaneously with the electrolyte.

[0042] The water soluble encapsulant for use according to our invention may be a water soluble film-forming organic macromolecule such as a polymer or gum. We particularly prefer a water soluble polyvinyl pyrrolidone.

[0043] We can also use a polyvinyl alcohol, a cellulose derivative such as carboxymethyl cellulose, methyl cellulose, or hydroxypropylcellulose, a lignin derivative such as lignin sulphonate, a gum such as guar gum, gum benzoin, gum tragacanth, gum arabic or gum acacia, a protein such as casein, gelatin or albumin, a carbohydrate such as starch, dextrose, galactose, or amylose, an amylopectin, or polycarboxylates such as polyacrylates or polymaleates. The encapsulant is preferably not a surfactant or poly glycol.

[0044] The water soluble encapsulant is preferably a water soluble polymer that is precipitated by electrolyte, to form a solid gelatinous or viscous film or coherent layer surrounding the dyestuff particles. The solution of the encapsulant may conveniently have a concentration of from 0.5% by weight of encapsulant based on the weight of the solution up to saturation.

[0045] Where a polymer such as, for example, polyvinyl pyrrolidone is used as the encapsulant we prefer to use a polymer with a molecular weight of from 10,000 to 1,500,000 e.g. 15,000 to 1,000,000 more preferably 20,000 to 900,000, especially 25,000 to 800,000. In the case of polyvinyl alcohol we particularly prefer polymers with a molecular weight of 18,000 to 140,000 preferably 50,000 to 120,000 e.g. 80,000 to 100,000.

[0046] Preferably any polyvinylalcohol used according to our invention is a partially hydrolysed polyvinyl ester of a lower (e.g. C<sub>1</sub> to 4) carboxylic acid, especially polyvinyl acetate, which has a degree of hydrolysis of greater than 25%, and desirably less than 95% especially 50 to 90% more preferably 60 to 80% e.g. 70% to 75%.

#### **Other Ingredients**

[0047] We prefer that the suspensions of our invention should have low foaming properties. While this can be achieved by selecting inherently low foaming surfactants, we generally prefer to include antifoams such as silicone oil antifoams, phosphate esters, fatty alcohols or hydrocarbon oils. Typically the antifoam is present in concentrations of 0.01 to 5% e.g. 0.05 to 1% by weight.

[0048] The composition may optionally include a suspending agent such as carboxymethyl cellulose or polyvinyl pyrrolidone, e.g. in amounts of from 0.1 to 5% preferably 0.5 to 2% by weight and a dispersing agent such as a ligno-sulphonate, alkyl naphthalene sulphonate or polyacrylate, e.g. in an amount of up to 10% by weight.

[0049] The composition may also, optionally, contain synergists, preservatives, buffers, antifreezes and fragrances.

[0050] We prefer that the composition does not contain any organic solvents, either water miscible solvents such as lower mono or polyhydroxy alcohols, ketones and polyethers or water-immiscible solvents such as aromatic hydrocarbons, nor any hydrotropes such as urea, benzene sulphonate or lower alkyl benzene sulphonates. Solvents and hydrotropes tend to interfere with surfactant structuring and require the use of substantially increased amounts of surfactant and/or electrolyte. They also increase the cost of the formulation without generally increasing performance. Aromatic solvents are in addition undesirable on toxicity grounds. We therefore prefer, if present at all, that solvents and hydrotropes are each present in proportions less than 10%, more preferably less than 5%, most preferably less than 1%, e.g. less than 0.5%, usually less than 0.1% and most commonly less than 0.05% by weight.

[0051] We similarly prefer that polymeric thickening agents such as gums are absent or present in concentrations less than 5%, preferably less than 0.5% since they are not generally necessary to stabilise the compositions and since they increase the cost and viscosity of the suspensions.

[0052] The invention will be illustrated by the following examples in which all percentages are by weight based on total weight.

#### Example 1

[0053] A concentrated dispersion was made up from :

Water	31%
Disperse orange azo dye	25%
Sodium salt of C <sub>10-12</sub> linear alkyl benzene sulphonic acid (LABS)	33.3%
Sodium salt of the sulphate ester of the triethoxylate of C <sub>12</sub> alcohol (KSN)	7.1%
Potassium chloride	3%
Silicone defoamer	0.1%
Sodium ligno sulphonate	0.5%

#### Example 2

[0054] A concentrated dispersion was made up from:

Water	29.5%
Disperse orange azo dye	25%
LABS	33.3%
KSN	7.1%
Potassium Chloride	3%
Silicone defoamer	0.1%
Polyacrylate " sold under the Registered Trade Mark "BEVALOID" 207	2%

#### Example 3

[0055] A concentrated dispersion was made up from:

Water	51.9%
Orange azo dye	35%
Iso propylamine salt of dodecyl benzene sulphonic acid (isopropylamine LABS)	12.6%
Silicone defoamer	0.1%
Sodium lignosulphonate	1%

#### Example 4

[0056] A concentrated dispersion was made up from:

Water	33.6%
-------	-------

(continued)

Orange azo dye	35%
LABS	20%
Coconut diethanolamide (CDE)	6%
Sodium Nitrate	4%
Silicone defoamer	0.1%
polyacrylate	1.3%

**Example 5**

[0057] A concentrated dispersion was made up from:

Water	29.9%
Orange azo dye	35%
LABS	26.7%
CDE	4%
NaNO <sub>3</sub>	3%
Silicone defoamer	0.1%
Sodium salt of dibutyl naphthalene sulphonic acid	1.3%

**Example 6**

[0058] A concentrated dispersion was made up from:

Orange azo dye	25%
Isotridecyl alcohol 8 mole ethoxylate	1.1%
Isopropylamine LABS	5.6%
Sodium salt of methyl naphthalene sulphonic acid formaldehyde condensate (MNSF)	1.5%
Silicone defoamer	0.06%
Water	68.74%

**Example 7**

[0059] A concentrated dispersion was made up from:

Orange azo dye	23%
Triethanolamine salt of phosphated tristylphenol 17 mole ethoxylate	1.6%
Isopropylamine LABS	7.4%
MNSF	1.5%
Silicone defoamer	0.06%
Water	66.44%

**Example 8**

[0060] A concentrated dispersion was made up from:

Blue anthraquinone disperse dye	14.5%
isopropylamine LABS	9.5%
MNSF	1.5%
Silicone defoamer	0.1%
Water	74.4%

[0061] All the foregoing Examples formed stable dispersions which dispersed well on pouring into a large quantity

of cold water.

#### Example 9

5 [0062] A printing paste was prepared comprising:

Blue anthraquinone dye	6%
Isopropylamine LABS	12%
MNSF	0.15%
Water	81.85%

10

#### Example 10

15 [0063] A printing paste was prepared comprising:

Orange azo dye	4%
Isotridecyl alcohol 8 mole ethoxylate	19%
Isopropylamine LABS	9.5%
Ammonium orthophosphate	4%
Sodium Lignosulphonate	0.1%
Silicone defoamer	0.1%
Water	63.3%

20

25

#### Example 11

[0064] A printing paste was prepared comprising:

Blue dye	2%
Isopropylamine LABS	18%
Sodium naphthalene sulphonate	0.1%

30

35 The products of examples 9, 10 and 11 had good stability and rheological properties, and excess was readily removed on rinsing.

#### Example 12

40 [0065] A mixture of disodium salt of 4;4'-[di(styryl-2-sulphonic acid)] biphenyl and the di sodium salt of 4;4'-[di(4-chlorostyryl-3-sulphonic acid)] biphenyl sold commercially for use as an OBA by Ciba-Geigy under the Registered Trade-mark "TINOPAL" ATS-X was suspended in a composition comprising:

LABS	11.5%
coconut monoethanolamide	1.5%
"TINOPAL" ATS-X	35.0
sodium silicate	6.0
water	balance

45

50 [0066] The surfactant and silicate were mixed in the above relative proportions, together with the minimum amount of water to maintain a stirrable composition. The OBA was then gradually stirred in, adding just sufficient water with each addition of OBA, to maintain a stirrable mixture. Finally the mixture was diluted with water, to a convenient viscosity for handling. In order to obtain an optimum combination of viscosity and storage stability it is preferred to prepare a series of samples at different dilutions and to test them for storage stability e.g. by standing at ambient temperature  
55 for three months. The more dilute compositions show signs of instability while the more concentrated show good stability but higher viscosity.



**Example 13-16**

[0067] Suspensions of OBA solid under the Registered Trade Mark "TINOPAL" LMS/X were prepared according to the following table.

Example	13	14	15	16
OBA	30	30	25	20
isopropylamine LABS	8	8	-	8
MNSF	-	1	-	1
30% LABS aqueous solution	-	-	33	-
KSN	-	-	7.1	-
potassium chloride	-	-	3	-
silicone defoamer	-	-	0.1	-
water	62	61	31.8	71

**Claims**

1. A dye suspension comprising 2% to 50% by weight of particles or droplets of a sparingly water soluble or substantially water-insoluble dye stably dispersed in a pourable medium; ~~characterised in that:~~ said medium comprises water, at least 2% by weight based on the total weight of the composition of surfactant and, if required, sufficient of a surfactant desolubilising electrolyte, to form with said surfactant a structured surfactant system comprising a G-phase or a dispersion of surfactant mesophase, lamellar solid, or multilayered spherulites so as to confer thixotropic and solid-suspending properties.
2. A dye suspension according to Claim 1 wherein said aqueous structured surfactant comprises surfactant spherulites interspersed with an aqueous phase.
3. A dye suspension according to Claim 1 wherein said aqueous structured surfactant comprises an open lamellar structure interspersed with an aqueous phase.
4. A dye suspension according to any foregoing claim comprising from 2 to 65% by weight of surfactant based on the total weight of the composition.
5. A dye suspension according to Claim 4 comprising from 4 to 50% by weight of surfactant.
6. A dye suspension according to any foregoing claim further comprising from 1 to 50% by weight on the total weight of the composition of dissolved surfactant desolubilising electrolyte.
7. A suspension according to Claim 6 comprising from 2 to 15% by weight of said dissolved surfactant desolubilising electrolyte.
8. A dye suspension according to any foregoing claim, comprising from 15 to 40% by weight, based on the total weight of the composition, of said dye, and further wherein said dye is a disperse dye and said composition is dispersed in water to form a dyebath.
9. A dye suspension according to any foregoing claim, comprising from 2 to 15% by weight, based on the total weight of said composition, of said dye and further wherein said dye is a disperse dye, and said composition is a printing paste.
10. The dye composition according to any foregoing claim, comprising from 15 to 40% by weight, based on the total weight of the composition, of said dye and further wherein said dye is an optical brightening agent, and said composition is for use in the manufacture of detergents.
11. A dye suspension according to any foregoing claim consisting essentially of:

(1) an aqueous structured surfactant comprising:

- (i) water, and
- (ii) 2 to 65% by weight, based on the total weight of the composition, of surfactant, and
- (iii) 0 to 50% by weight, based on the total weight of the composition, of a dissolved surfactant desolubilising electrolyte

and

(2) from 2 to 50% by weight, based on the total weight of the composition, of solid particles of a substantially water insoluble or sparingly soluble dye.

#### Patentansprüche

1. Farbstoffsuspension, die 2 bis 50 Gew.-% Teilchen oder Tröpfchen eines in Wasser mäßig löslichen oder in Wasser weitgehend unlöslichen Farbstoffes in einem gießbaren Medium beständig dispergiert enthält, dadurch gekennzeichnet, daß dieses Medium enthält:
  - Wasser,
  - wenigstens 2 Gew.-% Tensid, bezogen auf das Gesamtgewicht der Zusammensetzung, und
  - sofern erforderlich, eine ausreichende Menge eines das Tensid weniger löslich machenden Elektrolyten, um zusammen mit dem Tensid ein strukturiertes Tensidsystem zu bilden, das eine G-Phase oder eine Dispersion von Tensid-Mesophase oder einen lamellaren Feststoff oder mehrschichtige Sphäroliten, aufweist, um der Zusammensetzung thixotrope und Feststoff-suspendierende Eigenschaften zu erteilen.
2. Farbstoffsuspension nach Anspruch 1, dadurch gekennzeichnet, daß dieses wässrige strukturierte Tensid Tensid-Sphäroliten aufweist, die in einer wässrigen Phase verteilt sind.
3. Farbstoffsuspension nach Anspruch 1, dadurch gekennzeichnet, daß dieses wässrige strukturierte Tensid eine offene, lamellare Struktur aufweist, die in der wässrigen Phase verteilt ist.
4. Farbstoffsuspension nach einem der Ansprüche 1 bis 3, dadurch gekennzeichnet, daß der Gehalt an Tensid 2 bis 65 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung.
5. Farbstoffsuspension nach Anspruch 4, dadurch gekennzeichnet, daß der Gehalt an Tensid 4 bis 50 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung.
6. Farbstoffsuspension nach einem der Ansprüche 1 bis 5, dadurch gekennzeichnet, daß der Gehalt an das gelöste Tensid weniger löslich machendem Elektrolyten 1 bis 50 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung.
7. Farbstoffsuspension nach Anspruch 6, dadurch gekennzeichnet, daß der Gehalt an das gelöste Tensid weniger löslich machendem Elektrolyten 2 bis 15 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung.
8. Farbstoffsuspension nach einem der Ansprüche 1 bis 7, dadurch gekennzeichnet, daß der Gehalt an Farbstoff 15 bis 40 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung; und dieser Farbstoff ein Dispersionsfarbstoff ist; und die Zusammensetzung in Wasser dispergiert ist, um ein Färbepad zu bilden.

9. Farbstoffsuspension nach einem der Ansprüche 1 bis 7,  
dadurch gekennzeichnet, daß

der Gehalt an Farbstoff 2 bis 15 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung;  
dieser Farbstoff ein Dispersionsfarbstoff ist; und  
die Zusammensetzung eine Druckpaste bildet.

10. Farbstoffsuspension nach einem der Ansprüche 1 bis 7,  
dadurch gekennzeichnet, daß

der Gehalt an Farbstoff 15 bis 40 Gew.-% ausmacht, bezogen auf das Gesamtgewicht der Zusammensetzung;  
dieser Farbstoff ein optisches Aufhellungsmittel ist; und  
die Zusammensetzung zur Herstellung von Detergentien eingesetzt wird.

11. Farbstoffsuspension nach einem der Ansprüche 1 bis 10,  
dadurch gekennzeichnet, daß  
diese Farbstoffsuspension im wesentlichen besteht aus:

(1) einem wässrigen, strukturierten Tensid, das seinerseits enthält:

(I) Wasser, und

(II) 2 bis 65 Gew.-% Tensid, bezogen auf das Gesamtgewicht der Zusammensetzung, und

(III) 0 bis 50 Gew.-% das gelöste Tensid weniger löslich machenden Elektrolyten, bezogen auf das Gesamtgewicht der Zusammensetzung; und

(2) 2 bis 50 Gew.-% Feststoffpartikel aus einem in Wasser weitgehend unlöslichen oder mäßig löslichen Farbstoff, bezogen auf das Gesamtgewicht der Zusammensetzung.

## Revendications

1. Une suspension de colorant comprenant 2 à 50 % en poids de particules ou de gouttelettes d'un colorant modérément soluble ou largement insoluble dans l'eau, dispersées de manière stable dans un milieu coulant, caractérisée en ce que ledit milieu comprend de l'eau, au moins 2 % en poids de tensioactif par rapport au poids total de la composition et, si nécessaire, une proportion suffisante d'un électrolyte désolubilisant le tensioactif, pour former avec ce dernier un système de tensioactif structuré comprenant une phase G ou une dispersion de mésophase de surfactif, de sphérulites lamellaires solides ou multicouches, de manière à conférer des propriétés thixotropes et de mise en suspension de matières solides.
2. Une suspension de colorant selon la revendication 1, dans laquelle ledit tensioactif structuré aqueux comprend des sphérulites de surfactif entremêlés avec une phase aqueuse.
3. Une suspension de colorant selon la revendication 1, dans laquelle ledit tensioactif structuré aqueux comprend une structure lamellaire ouverte entremêlée avec une phase aqueuse.
4. Une suspension de colorant selon n'importe laquelle des revendications qui précèdent comprenant 2 à 65 % en poids de tensioactif par rapport au poids total de la composition.
5. Une suspension de colorant selon la revendication 4, comprenant 4 à 50 % en poids de tensioactif.
6. Une suspension de colorant selon n'importe laquelle des revendications qui précèdent comprenant 1 à 50 % en poids, par rapport au poids total de la composition, d'électrolyte désolubilisant le tensioactif dissous.
7. Une suspension selon la revendication 6, comprenant 2 à 15 % en poids dudit électrolyte désolubilisant le tensioactif dissous.
8. Une suspension de colorant selon n'importe laquelle des revendications qui précèdent comprenant 15 à 40 % en poids, par rapport au poids total de la composition, dudit colorant, et en outre dans laquelle ledit colorant est un

colorant de dispersion et ladite composition est dispersée dans l'eau pour former un bain de teinture.

- 5 9. Une suspension de colorant selon n'importe laquelle des revendications qui précèdent comprenant 2 à 15 % en poids, par rapport au poids total de ladite composition, dudit colorant et en outre dans laquelle ledit colorant est un colorant de dispersion et ladite composition est une pâte d'impression.
- 10 10. La suspension de colorant selon n'importe laquelle des revendications qui précèdent comprenant 15 à 40 % en poids, par rapport au poids total de la composition, dudit colorant et en outre dans laquelle ledit colorant est un agent de blanchiment optique, et ladite composition est destinée à être utilisée dans la production de détersifs.
11. Une suspension de colorant selon n'importe laquelle des revendications qui précèdent se composant essentiellement de:
- 15 (1) un tensioactif structuré aqueux comprenant:
- (i) de l'eau et
- (ii) 2 à 65 % en poids, par rapport au poids total de la composition, de tensioactif et
- (iii) 0 à 50 % en poids, par rapport au poids total de la composition, d'un électrolyte désolubilisant le
- 20 tensioactif dissous
- et
- (2) 2 à 50 % en poids, par rapport au poids total de la composition, de particules solides d'un colorant largement insoluble ou modérément soluble dans l'eau.